



Date of issue : 05/01/2005
Last. mod. date : 14/05/2009

Product code**03817 RI-757/60 PP CAVITATED WHITE TC RP 1101 WG 65****Description**

Gloss, white cavitated polypropylene film, top coated to guarantee a good printability.

Printing methods: UV letterpress, UV screen, UV flexo, gravure and hot stamping

Permanent, rubber based adhesive with high adhesion on apolar substrates such as polyethylene and polypropylene.

In case of transparent film the direct exposure to sunlight or UV light can lead to adhesive degradation or yellowness. Applications: high quality labels for plastic containers and bottles.

FACE MATERIAL

| | |
|-------------------|-----------------------------|
| Type | Cavitated polypropylen film |
| Colour and Finish | Bright white |
| Weight | 43 g/m ² |
| Thickness | 60 μ |

ADHESIVE

| | |
|------------------|------------------------|
| Reference | RP 1101 |
| Type | Rubber permanent |
| Min. Appl. Temp. | 0 °C |
| Service Temp. | -10 °C/+70 °C |
| Shear | Very high |
| Tack FTM9 | 19 N/inch ² |
| FinAdh FTM2 | 14 N/inch |

RELEASE BACKING

| | |
|-------------------|-----------------------------|
| Type | 1 side siliconised glassine |
| Colour and Finish | White |
| Weight | 63 g/m ² |
| Thickness | 56 μ |
| Transparency | >47 % |

Storage

The material must be stored at a temperature of 22°C +/- 2°C and 50% +/- 5% of Relative Humidity. Do not expose to direct sun light.

The area must be dry and clean. Please keep the material in the original packaging when not used in order to protect it from dust and contaminations.

All values presented in this data sheet are typical. Ritrama's data sheets provide only the general characteristics of the Product. It is the responsibility of the Customer and/or End User to determine that the Product is fit for the purpose for which the Customer and/or End User wish to use it. Ritrama can give no guarantee beyond the information given in the data sheet.

Ritrama S.p.A.
Ritrama S.p.A. Sassoferrato
Coating Ricofin S.r.l.
Ritrama S.A.
Ritrama Ltd.(UK)
Ritrama Inc. Minneapolis (USA)
Ritrama Inc. Cleveland (USA)

Tel. +39 02 955 459 1
Tel. +39 0732 97061
Tel. +39 02 955 430 1
Tel. +34 93 729 49 98
Tel. +44 161 786 1760
Tel. +1 612 378 2277
Tel. +1 216 851 2300

info@ritrama.it
info@ritrama.it
info@ricofin.it
ritrama@ritrama.es
sales@ritrama.co.uk
info@ritrama.com
info@ritrama.com