



Date of issue : 05/01/2005

Last. mod. date : 11/06/2009

Product code**02131 TRIPLEX VELLUM SC AP 904 WG 65/WG 62****Description**

A triplex-construction with two glassine liners. The face material is a white calandered woodfree paper.

It is printable by flexo, letterpress, offset and also by selected ribbons in thermal transfer.

In both layers a permanent acrylic adhesive for applications on a wide variety of surfaces.

For office and administration documents.

Technical data**FACE MATERIAL**

| | |
|-------------------|--------------------|
| Type | Calandered paper |
| Colour and Finish | White |
| Weight | 73g/m ² |
| Thickness | 72μ |

ADHESIVE

| | |
|------------------|-----------------------|
| Reference | AP 904 |
| Type | Acrylic permanent |
| Min. Appl. Temp. | + 5 °C |
| Service Temp. | -40°C/+100°C |
| Shear | Medium |
| Tack FTM9 | 11N/inch ² |
| FinAdh FTM2 | 13N/inch |

RELEASE BACKING

| | |
|-------------------|--------------------|
| Type | Glassine paper |
| Colour and Finish | White |
| Weight | 63g/m ² |
| Thickness | 56μ |

ADHESIVE

| | |
|------------------|-----------------------|
| Reference | AP 904 |
| Type | Acrylic permanent |
| Min. Appl. Temp. | + 5 °C |
| Service Temp. | -40°C/+100°C |
| Shear | Medium |
| Tack FTM9 | 11N/inch ² |
| FinAdh FTM2 | 13N/inch |

RELEASE BACKING

| | |
|-------------------|--------------------|
| Type | Glassine paper |
| Colour and Finish | Yellow |
| Weight | 62g/m ² |
| Thickness | 55μ |

Storage

The material must be stored at a temperature of 22°C +/- 2°C and 50% +/- 5% of Relative Humidity. Do not expose to direct sun light.

The area must be dry and clean. Please keep the material in the original packaging when not used in order to protect it from dust and contaminations.

All values presented in pdf data sheet are typical. Ritrana's data sheets provide only the general characteristics of the Product. It is the responsibility of the Customer and/or End User to determine that the Product is fit for the purpose for which the Customer and/or End User wish to use it. Ritrana can give no guarantee beyond the information given in the data sheet.